

Heubach formulation No. 02236

03/02

FUNCTION	PRODUCT	PRODUCER	PBW
Polyester	Polymac 935	Eastman	21.20
Melamine resin	Cymel 303LF, 100%	Cytec	5.90
Solvent	High Flash Naptha		3.90
Titanium dioxide	Tiona RCL-535	Millenium Inorganic Chemicals	26.50
Anticorrosive pigment	HEUCOPHOS® SRPP	Heubach	5.90
Grind with a bead mill.			
Polyester	Polymac 935	Eastman	30.20
Catalyst	Cycat 4040	Cytec	0.50
Levelling agent	Byk-370	Byk-Chemie	2.00
Solvent	High Flash Naptha		3.90
Add while mixing.			
			100.00

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.