

Calcium Phosphate CP

In short oil alkyd



Solvent based

Heubach formulation No. 06272

06/06

FUNCTION	PRODUCT	PRODUCER	PBW
Short oil alkyd	Vialkyd AF 342n/60X	Cytec	38.20
Aromatic hydrocarbon	Xylene		14.00
Glycol ether	Dowanol PM	CG Chemikalien	1.80
Drier	Octa-Soligen Calcium 10	Borchers	0.10
Premix.			
Aromatic hydrocarbon	Xylene		3.40
Wetting and Dispersing agent	Anti-Terra-204	Byk-Chemie	0.20
Rheology modifier	Bentone 34	Elementis	0.40
Mix until uniform paste prior to addition.			
Anticorrosive pigment	Calcium Phosphate CP	Heubach	9.35
Magnesium silicate	Westmin 8	Mondo Minerals	10.20
Barium sulphate	Albaryt	Sachtleben	15.05
Titanium dioxide	Kemira 650	Kemira	6.00
Grind.			
Lead-free drier	Octa-Soligen Drier 173	Borchers	1.10
Antiskinning agent	Borchinox M 2	Borchers	0.20
Add components separately while mixing.			
			100.00
SPECIFICATIONS			
PVC / CPVC			0.7
Solids in %			64.0
Vol.-% Anticorrosive pigment reg. pigment/filler			30.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.