

FUNCTION	PRODUCT	PRODUCER	PBW
Alkyd emulsion	Synthalat W 50, 38%	Synthopol Chemie	49.60
	Water		6.20
Anticorrosive pigment	HEUCOPHOS® ACP	Heubach	7.60
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	8.05
Calcium carbonate	Millicarb BG	Omya	5.75
Iron oxide red	Bayferrox 222 FM	Lanxess	7.20
Antisettling agent	Aerosil R 972	Degussa, today Evonik	1.20
Drier	Servosyn WEB Cobalt 8%, today Nuodex WEB Cobalt 8%	Servo, today Condea Servo	0.20
Drier	Servosyn WEB Manganese 9%, today Nuodex WEB Manganese 9%	Servo, today Condea Servo	0.20
Wetting agent	Surfynol 104 E	Air Products	0.55
Grind.			
	Water		12.50
Flash-rust inhibitor	Ser-AD FA 179	Servo, today Condea Servo	0.55
Antiskinning agent	Exkin 2	Servo, today Condea Servo	0.20
Wetting agent	Bayowet FT 448	Borchers	0.20
Add while mixing. Adjust pH 8.3 with ammonia, 10%.			
			100.00
SPECIFICATIONS			
Solids in %			48.6
Vol.-% Anticorrosive pigment reg. pigment/filler			30.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.