

FUNCTION	PRODUCT	PRODUCER	PBW
Alkyd emulsion	Resydrol AZ 436 w/45 WA	Vianova Resins, today Cytec	55.50
Neutralizing agent	Ammonia, 10%		1.00
Drier	Additol VXW 4940, 50% in H ₂ O	Vianova Resins, today Cytec	1.30
Antiskinning agent	Additol XL 297	Vianova Resins, today Cytec	0.30
Wetting agent	Surfynol SE-F	Air Products	0.30
Defoamer	Additol VXW 4973	Vianova Resins, today Cytec	0.30
	Water		12.90
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	5.50
Corrosion inhibitor	Sicorin RZ, today HEUCORIN® RZ	BASF, today Heubach	0.60
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	8.20
Calcium carbonate	Millicarb BG	Omya	5.30
Iron oxide red	Bayferrox 222 FM	Bayer	6.50
Grind with a bead mill.			
PU-thickener	Rheolate 225	Elementis	2.00
Neutralizing agent	AMP-90	Angus Chemie	0.30
Add to the grind. Adjust pH 9.0 - 9.5 with ammonia, 10%.			
			100.00
SPECIFICATIONS			
PVC in %			25.2
PVC / CPVC			0.5
Solids in %			52.7
Vol.-% Anticorrosive pigment reg. pigment/filler			19.5

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.