

HEUCOPLEX Z 30

In short oil alkyd



Solvent based

Heubach formulation No. 528

03/15

FUNCTION	PRODUCT	PRODUCER	PBW
Short oil alkyd	WorléeKyd SM 433/60X	Worlée	31.65
Solvent	Solvesso 100	Exxon	22.10
Glycol ether	Dowanol PM	CG Chemikalien	2.00
Antisettling agent	Aerosil 300	Evonik	0.30
Premix.			
Aromatic hydrocarbon	Xylene		2.60
Rheology modifier	Bentone 38	Elementis	0.30
Wetting and Dispersing agent	Anti-Terra-204	Byk-Chemie	0.10
Mix until uniform paste prior to addition.			
Drier	Octa-Soligen Calcium 5	Borchers	0.50
Anticorrosive pigment	HEUCOPLEX Z 30	Heubach	10.35
Titanium dioxide	Kronos 2190	Kronos	4.85
Mica/Quartz/Chlorite	Plastorit M	Imerys Talc	4.85
Iron oxide black	Bayferrox 316	Lanxess	0.45
Magnesium silicate	Finntalc M15	Mondo Minerals	11.60
Magnesium calcium carbonate	Microdol Extra	Mondo Minerals	7.75
Grind with a bead mill.			
Drier	Octa-Soligen Cobalt 6	Borchers	0.10
Drier	Octa-Soligen Calcium 10	Borchers	0.20
Antiskinning agent	Exkin 2	Elementis	0.30
Add while mixing.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0
PVC / CPVC			0.8

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.