

Heubach formulation No. 881-07

03/18

FUNCTION	PRODUCT	PRODUCER	PBW
Alkyd emulsion	Resydrol AZ 436 w/45 WA	Allnex	55.30
Neutralizing agent	Ammonia, 10%		1.00
	Demi. water		13.10
Wetting agent	Borchi Gen 1253	Borchers	2.95
Defoamer	Borchers AF 1171	Borchers	0.30
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Heubach	5.50
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.60
Magnesium silicate	Finntalc M05	Mondo Minerals	8.10
Calcium carbonate	Durcal 2	Omya	5.30
Iron oxide red	Bayferrox 130 M	Lanxess	6.40
Grind with a bead mill.			
PU-thickener	Borchi Gel 0626	Borchers	1.00
Drier	Borchi OXY-Coat 1101	Borchers	0.15
Neutralizing agent	AMP-90	Angus Chemie	0.30
Add while mixing. Adjust pH 8.5 - 9.3 with ammonia.			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0
PVC in %			25.9
PVC / CPVC			0.5
Solids in %			50.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.