

Heubach formulation No. 00188

09/00

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Curing agent	Beckopox EH 613 w/80 WA	Solutia, today Cytec	5.50
	Water		19.10
Wetting agent	Additol XL 270	Solutia, today Cytec	0.60
Wetting agent	Surfynol SE-F	Air Products	0.60
Premix.			
Magnesium aluminium silicate	Plastorit M	Naintsch, today Luzenac	9.50
Anticorrosive pigment	HEUCOPHOS® SRPP	Heubach	5.20
Titanium dioxide	Kemira 650	Kemira	13.55
Iron oxide yellow	Bayferrox 3910	Bayer	3.70
Chromium oxide green	Chromoxidgrün GN-M	Bayer	0.30
Grind with a bead mill, temperature < 104°F.			
Thickener	Deuteron VT 819	Schöner	0.05
Add while mixing.			
			58.10
Component B			
Epoxy dispersion	Beckopox EP 385 w/56 WA	Solutia, today Cytec	41.90
Mix.			
			41.90
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
PVC in %			28.6
PVC / CPVC			0.5
Solids in %			60.7

HEUCOPHOS[®] SRPP

in epoxy dispersion



Water based

Heubach formulation No. 00188

09/00

SPECIFICATIONS

Vol.-% Anticorrosive pigment reg. pigment/filler

20.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.