

Heubach formulation No. 99151

08/99

FUNCTION	PRODUCT	PRODUCER	PBW
Long oil alkyd	Beckosol 10-060, 70%	Reichhold	31.10
Load.			
Solvent	White spirit		14.30
Rheology modifier	Bentone 34	Elementis	1.00
Solvent	Methyl alcohol		0.20
Mix until uniform paste prior to addition.			
Iron oxide red	Bayferrox 222 FM	Bayer	7.20
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	9.60
Magnesium silicate	Beaverwhite 325	Cyprus Industrial Minerals	23.90
Grind.			
Long oil alkyd	Beckosol 10-060, 70%	Reichhold	7.20
Solvent	White spirit		4.30
Drier	Zirconium Chem-All 12%	Mooney Chemicals	0.30
Drier	Cobalt Chem-All 12%	Mooney Chemicals	0.10
Drier	Zinc Chem-All 8%	Mooney Chemicals	0.40
Drier	Calcium Chem-All 4%	Mooney Chemicals	0.20
Antiskinning agent	Skino #1	Mooney Chemicals	0.20
Add components separately while mixing.			
			100.00
SPECIFICATIONS			
PVC in %			37.2
Solids in %			68.9
Vol.-% Anticorrosive pigment reg. pigment/filler			23.4

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.