

Heubach formulation No. 06271

06/06

FUNCTION	PRODUCT	PRODUCER	PBW
High solids alkyd	BECKOSOL 6440-A4-85	Reichhold	12.50
Titanium dioxide	Ti-Pure Rutile R-902	DuPont	22.30
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Heubach	10.00
Aromatic hydrocarbon	Xylene		6.00
Grind.			
High solids alkyd	BECKOSOL 6440-A4-85	Reichhold	32.90
Drier	Nuodex Cobalt 6%	Elementis	0.30
Drier	Nuodex Zirconium 12%	Elementis	0.30
Drier	Nuodex Calcium 4%	Elementis	0.60
Antiskinning agent	Exkin 2	Elementis	0.10
Aromatic hydrocarbon	Xylene		15.00
Add components separately while mixing.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			33.2

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.