

Calcium Phosphate CP

In shop primer



Solvent based

Heubach formulation No. 06275

06/06

FUNCTION	PRODUCT	PRODUCER	PBW
Polyvinyl butyral	Mowital B 30 HH, 100%	Clariant, today Kuraray Specialities	11.00
Solvent	Butyl alcohol		14.00
Aromatic hydrocarbon	Xylene		17.00
Solvent	Isopropyl alcohol		20.00
Mix until uniform solution prior to addition.			
Epoxy	Beckopox EP 301/75X	Cytec	5.30
Glycol ether	Dowanol PM	CG Chemikalien	2.70
Titanium dioxide	Kronos 2190	Kronos	21.00
Mix until uniform paste prior to addition.			
Aromatic hydrocarbon	Xylene		4.25
Antisettling agent	Wacker HDK H 15	Wacker	0.50
Wetting agent	Additol XL 270	Cytec	0.25
Mix until uniform paste prior to addition.			
Anticorrosive pigment	Calcium Phosphate CP	Heubach	4.00
Grind.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.