

Heubach formulation No. 135-03

07/07

FUNCTION	PRODUCT	PRODUCER	PBW
Polyurethane copolymerisate dispersion	Bayhydrol B 130, 30%	Bayer	64.10
Antiskinning agent	Borchinox M 2	Borchers	0.30
Drier	Nuodex WEB Cobalt 8%	Elementis	0.20
Glycol ether	Butyl glycol		1.00
Drier	Aluminium octoate	Tropag	0.10
<b>Premix.</b>			
Calcium carbonate	Millicarb	Omya	5.10
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	10.70
Iron oxide red	Bayferrox 130 M	Bayer	10.60
Anticorrosive pigment	HEUCOPHOS® ZAPP	Heubach	7.70
Antisettling agent	Aerosil 200	Degussa, today Evonik	0.20
<b>Grind with a bead mill, temperature &lt; 40 °C.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			25.0
PVC in %			34.5
PVC / CPVC			0.7
Solids in %			54.1

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.