

Heubach formulation No. 744-07

07/14

FUNCTION	PRODUCT	PRODUCER	PBW
Polyvinyl butyral	Mowital B 30 H, 100%	Kuraray Europe GmbH	10.80
Solvent	N-Butyl alcohol		60.70
Aromatic hydrocarbon	Xylene		22.10
<b>Mix until uniform solution prior to addition.</b>			
Anticorrosive pigment	HEUCOPHOS® CMP	Heubach	4.60
Magnesium silicate	Finntalc M15	Mondo Minerals	1.40
Antisettling agent	Aerosil R 972	Evonik	0.40
<b>Grind with a bead mill.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			70.0
PVC in %			19.4
PVC / CPVC			0.4
Solids in %			17.2

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.