

Heubach formulation No. 99153

08/99

FUNCTION	PRODUCT	PRODUCER	PBW
Phenolic modified high solids alkyd	Rezamac H.S. 57-5703	McWhorter, today Eastman	16.50
Solvent	Butyl acetate		1.15
Premix.			
Rheology modifier	Bentone SD-2	Elementis	0.20
Iron oxide red	Bayferrox 222 FM	Lanxess	20.65
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	8.00
Calcium carbonate	Snowflake	ECC International, today Imerys	14.40
Magnesium silicate	Beaverwhite 325	Cyprus Industrial Minerals	7.50
Aromatic hydrocarbon	Xylene		2.75
Grind.			
Phenolic modified high solids alkyd	Rezamac H.S. 57-5703	McWhorter, today Eastman	19.40
Solvent	Butyl acetate		7.20
Drier	Cobalt Chem-All 12%	Mooney Chemicals	0.10
Drier	Zirconium Chem-All 18%	Mooney Chemicals	0.45
Drier	Calcium Chem-All 8%	Mooney Chemicals	0.15
Antiskinning agent	Skino #1	Mooney Chemicals	0.15
Aromatic hydrocarbon	Xylene		1.40
Add components separately while mixing.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			15.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.