

Heubach formulation No. 99162

09/99

FUNCTION	PRODUCT	PRODUCER	PBW
High solids alkyd	Cargill 57-5809, 85%	Cargill	9.30
Drier	Nuodex Calcium 4%	Condea Servo	0.80
Drier	Nuodex Zirconium 12%	Condea Servo	1.20
Solvent	White spirit		4.30
Premix.			
Titanium dioxide	Kronos 2160	Kronos	20.30
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	10.00
Grind.			
High solids alkyd	Cargill 57-5809, 85%	Cargill	41.00
Drier	Nuodex Cobalt 6%	Condea Servo	0.25
Stabilizer	Activ-8	R.T. Vanderbilt	0.15
Antiskinning agent	Exkin 2	Condea Servo	0.20
Solvent	White spirit		8.10
Solvent	n-Butyl alcohol		4.40
Add components separately while mixing.			
			100.00
SPECIFICATIONS			
Solids in %			76.0
Vol.-% Anticorrosive pigment reg. pigment/filler			32.6

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.