

Evonik Tego formulation No. PON EF 9 007

10/20

FUNCTION	PRODUCT	PRODUCER	PBW
Silicone epoxy hybrid resin	SILIKOPON EF	Evonik	30.00
Defoamer/Deaerator	Tego Airex 900	Evonik	1.00
Antisettling agent	AEROSIL R 972	Evonik	2.00
Titanium dioxide	KRONOS 2315	KRONOS	27.50
Barium sulphate	BLANC FIXE micro	Venator	3.00
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Heubach	3.80
Aromatic hydrocarbon	Xylene		1.00
Grind with a bead mill.			
Silicone epoxy hybrid resin	SILIKOPON EF	Evonik	14.50
Acrylic	DEGALAN LP 65/11, 45% in Butyl acetate	Evonik	11.00
Wetting agent	Tego Wet 270	Evonik	0.20
Light stabilizer	Tinuvin 292	BASF	0.50
Solvent	Butyl acetate		5.50
Add while stirring.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			11.4
PVC in %			19.4
Solids in %			87.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.