

Heubach formulation No. 02226

02/02

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		6.60
Wetting agent	Tamol 681	Rohm and Haas	0.65
Wetting agent	Surfynol 104 A	Air Products	0.20
Defoamer	Bubble Breaker 3056A	Witco, today Huntsman	0.10
PU-thickener	Acrysol RM-825	Rohm and Haas	0.10
<b>Premix.</b>			
Titanium dioxide	Ti-Pure Rutile R-706	DuPont	13.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	6.40
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.70
<b>Grind.</b>			
Acrylic	EPS-2504	Engineered Polymer Solutions	57.10
	Water		7.35
Neutralizing agent	Ammonia, 25%		0.20
Ester alcohol	Texanol	Eastman	7.10
Flash-rust inhibitor	Corrosion inhibitor L 1	Erbslöh	0.50
<b>Add while mixing.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Solids in %			46.2
Vol.-% Anticorrosive pigment reg. pigment/filler			32.9

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.