

Calcium Phosphate CP

In epoxy



Solvent based

Heubach formulation No. 06274

06/06

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy	Araldite GZ 7071, 75% in xylene	Huntsman	15.55
Epoxy	Eurepox 783, 100%	Witco, today Ciba	11.60
Defoamer	Byk-057	Byk-Chemie	0.40
Premix.			
Rheology modifier	Luvotix P 25 X	Lehmann & Voss	2.90
Anticorrosive pigment	Calcium Phosphate CP	Heubach	5.75
Filler	Talc		25.00
Filler	Barium sulphate		10.00
Pigment	Iron oxide		4.65
Wetting and Dispersing agent	Anti-Terra-U	Byk-Chemie	0.40
Grind.			
Solvent	Isobutyl alcohol		1.90
Solvent	Shellsol A	Shell	12.20
Add while mixing.			
			90.35
Component B			
Curing agent	Euredur 450, 100%	Huntsman	9.65
Add.			
			9.65
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
Solids in %			79.4

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.