

Heubach formulation No. 406-02

01/06

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Polyacrylic dispersion	Macrynal VSM 6299 w, 42%	Cytec	40.30
Wetting agent	EnviroGem AD 01	Air Products	0.75
Dispersing agent	Disperse-Ayd W 28	Elementis	1.65
Defoamer	Byk-011	Byk-Chemie	1.45
Flash-rust inhibitor	Corrosion inhibitor L 1	Erbslöh	0.45
Calcium carbonate	Omycarb 1T-AV	Omya	17.55
Calcium carbonate	Calcigloss X-OM	Omya	3.80
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	10.65
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	3.80
Titanium dioxide	Kronos 2310	Kronos	4.55
	Water		2.55
Grind with a bead mill, fineness of grind app. 20 microns.			87.50
Component B			
Curing agent	Desmodur XP 2410	Bayer	10.10
Dipropylene glycol dimethyl ether	Proglyde DMM	Dow	2.40
Mix.			12.50
Mix components A and B thoroughly prior to use.			100.00
SPECIFICATIONS			
PVC in %			37.0
PVC / CPVC			0.6
Solids in %			67.0

HEUCOPHOS[®] ZPA

in 2-part polyurethane



Water based

Heubach formulation No. 406-02

01/06

SPECIFICATIONS

Vol.-% Anticorrosive pigment reg. pigment/filler

25.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.