

Heubach formulation No. 675-09

10/15

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy	Beckopox EP 301/75X	Allnex	22.78
Epoxy	Beckopox EP 116, 100%	Allnex	1.15
Glycol ether	Dowanol PM	CG Chemikalien	6.19
Solvent	Methyl isoamyl ketone		1.55
Aromatic hydrocarbon	Xylene		8.77
Premix.			
Aromatic hydrocarbon	Xylene		4.59
Wetting and Dispersing agent	Anti-Terra-204	Byk-Chemie	0.05
Rheology modifier	Bentone 38	Elementis	0.26
Rheology modifier	Thixogel VP	Süd-Chemie	0.26
Mix until uniform paste prior to addition.			
Antisettling agent	Aerosil R 972	Evonik	0.44
Wetting and Dispersing agent	Anti-Terra-204	Byk-Chemie	0.52
Anticorrosive pigment	HEUCOPHOS® CMP	Heubach	7.76
Barium sulphate	Albaryt	Sachtleben	15.65
Titanium dioxide	Kronos 2190	Kronos	3.23
Carbon black	Flammruß 101	Evonik	0.04
Magnesium silicate	Finntalc M15	Mondo Minerals	14.56
			87.80
Grind with a bead mill.			
Component B			
Curing agent	Versamid 115/70X	IMCD Group	12.20
Mix.			
			12.20

Heubach formulation No. 675-09

10/15

FUNCTION	PRODUCT	PRODUCER	PBW
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0
PVC in %			34.0
PVC / CPVC			0.7

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.