

Heubach formulation No. 716-08

07/13

FUNCTION	PRODUCT	PRODUCER	PBW
	Demi. water		8.40
Wetting agent	Tergitol 15-S-40	Dow	0.15
Wetting agent	Orotan 165	Dow	0.75
Glycol ether	Dowanol PM	Dow	1.25
Defoamer	Byk-023	Byk-Chemie	0.20
Titanium dioxide	Tioxide TR-92	Huntsman	15.35
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	3.80
Iron oxide black	Bayferrox 318 M	Lanxess	0.25
Flash-rust inhibitor	Nalzin FA 379	Elementis	0.20
Grind with a bead mill.			
	Demi. water		6.85
Defoamer	Byk-024	Byk-Chemie	0.15
PU-thickener	Acrysol SCT-275	Dow	0.40
Ester alcohol	Texanol	Eastman	2.45
Wetting agent	Tergitol 15-S-40	Dow	0.95
Levelling agent	Byk-349	Byk-Chemie	0.20
Acrylic emulsion	Maincote 1200, 43%	Dow	57.40
Glycol ether	Dowanol PM	Dow	1.25
Add to the grind.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			20.8
PVC in %			17.2
PVC / CPVC			0.3
Solids in %			44.1

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.