

Heubach formulation No. 796-06

09/15

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Acrylic	Setalux A 870 BA, 70%	Nuplex Resins	40.70
Wetting and Dispersing agent	Disperbyk-110	Byk-Chemie	1.15
Levelling agent	Byk-358 N	Byk-Chemie	0.75
Defoamer	Byk-077	Byk-Chemie	1.15
Aromatic hydrocarbon	Xylene		3.70
Rheology modifier	Bentone 38	Elementis	0.35
Wetting and Dispersing agent	Anti-Terra-204	Byk-Chemie	0.10
Anticorrosive pigment	HEUCOPHOS® ACP	Heubach	4.40
Titanium dioxide	Tioxide TR-92	Huntsman	22.60
Grind with a bead mill, fineness of grind app. 20 microns.			
Light stabilizer	Tinuvin 292	BASF	0.40
Solvent	Eastman EEP	Eastman	7.00
Solvent	Eastman MAK	Eastman	3.30
Add to the grind.			
Component B			
Curing agent	Desmodur N 3300	Covestro	13.90
Adhesion promoter	Dynasylan Glymo	Evonik	0.50
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			20.5
PVC in %			15.8
PVC / CPVC			0.3
Solids in %			69.5

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.