

# HEUCOPHOS® ZPA / HEUCORIN® RZ

in UV/EB cured system



Water based

Bayer formulation No. FWO 4061

08/10

FUNCTION	PRODUCT	PRODUCER	PBW
Unsaturated aliphatic allophanate urethane acrylate	Desmolux XP 2740	Bayer	26.29
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	13.15
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	2.63
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.27
Tripropyleneglycol diacrylate	TPGDA		21.03
<b>Grind to a fineness of &lt; 10 microns.</b>			
Radiation curable additive	Ebecryl 168	Cytec	5.38
Pigment paste	Pinova Rot HP 1070	Pinova	3.49
Tripropyleneglycol diacrylate	TPGDA		11.89
Ethoxylated phenol monoacrylate	Photomer 4039	Cognis	11.89
Photoinitiator	Lucirin TPO-L	BASF	1.07
Photoinitiator	Darocur 1173	Ciba	2.91
<b>Add while mixing.</b>			
			<b>100.00</b>

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.