

# Calcium Phosphate CP

In epoxy ester



Solvent based

Heubach formulation No. 06293

08/06

| FUNCTION   | PRODUCT                              | PRODUCER         | PBW           |
|--|--------------------------------------|------------------|---------------|
| Epoxy ester                                      | WorléeDur 6311, 60%                  | Worlée           | 39.80         |
| Drier  | Octa-Soligen Calcium 10              | Borchers         | 0.20          |
| Wetting and Dispersing agent                     | Soja-Lecitin-Concentrate STA         | Lubrizol         | 0.20          |
| <b>Premix.</b>                                   |                                      |                  |               |
| Anticorrosive pigment                            | Calcium Phosphate CP                 | Heubach          | 7.35          |
| Titanium dioxide                                 | Kronos 2190                          | Kronos           | 13.75         |
| Magnesium silicate                               | Finntalc M15                         | Mondo Minerals   | 6.40          |
| Mica   | Micro Mica W 1                       | Mondo Minerals   | 5.50          |
| Magnesium calcium carbonate                      | Microdol Extra                       | Mondo Minerals   | 8.25          |
| <b>Grind.</b>                                    |                                      |                  |               |
| Rheology modifier                                | Bentone 34 paste, 60% in Exxsol D 60 | Elementis, Exxon | 4.00          |
| Drier  | Octa-Soligen Cobalt 6                | Borchers         | 0.15          |
| Drier  | Octa-Soligen Calcium 10              | Borchers         | 0.30          |
| Solvent  | Exxsol D 60                          | Exxon            | 10.00         |
| Glycol ether                                     | Dowanol DPM                          | CG Chemikalien   | 3.50          |
| Antiskinning agent                               | Exkin 2                              | Elementis        | 0.60          |
| <b>Add while mixing.</b>                         |                                      |                  | <b>100.00</b> |
| <b>SPECIFICATIONS</b>                            |                                      |                  |               |
| PVC / CPVC                                       |                                      |                  | 0.6           |
| Vol.-% Anticorrosive pigment reg. pigment/filler |                                      |                  | 20.0          |
| Solids in %                                      |                                      |                  | 68.0          |

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.