

# HEUCOPHOS® ZCP-PLUS / HEUCORIN® RZ

in UV/EB cured system



Water based

Heubach formulation No. 12361 in accordance to Bayer formulation No. FWO 4037-1

08/10

FUNCTION	PRODUCT	PRODUCER	PBW
Unsaturated aliphatic allophanate urethane acrylate	Desmolux XP 2666	Bayer	49.12
Radiation curable additive	Ebecryl 168	Cytec	4.11
Ethoxylated phenol monoacrylate	Photomer 4039	Cognis	16.39
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	22.35
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	5.47
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.60
Photoinitiator	Irgacure 2022	Ciba	1.96
<b>Grind.</b>			
			<b>100.00</b>

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.