

Heubach formulation No. 519-02

06/10

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		11.85
Glycol ether	Butyl glycol		1.00
Wetting and Dispersing agent	Tego Dispers 755 W	Evonik Tego Chemie	2.95
Defoamer	Tego Foamex K3	Evonik Tego Chemie	0.80
Antisettling agent	Aerosil R 972	Evonik	1.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	5.20
Magnesium silicate	Micro-Talc I.T. Extra	Mondo Minerals	7.80
Manganese ferrite	Bayferrox 303 T	Lanxess	13.00
Carbon black	Printex L	Evonik	1.25
Grind.			
Silicone resin	Silikophen P 40/W	Evonik Tego Chemie	55.15
Add while mixing.			
			100.00
SPECIFICATIONS			
PVC / CPVC			0.5
PVC in %			23.5
CPVC			47.0
Vol.-% Anticorrosive pigment reg. pigment/filler			18.1

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.