

## Wacker formulation

02/01

FUNCTION	PRODUCT	PRODUCER	PBW
Silicone resin	Silres MP 42 E	Wacker	25.00
Soluble alkyd	Resydrol AZ 248 w/60 SNAMP	Vianova Resins, today Cytec	25.00
	Water		25.00
Carbon black	Flammruß 101	Degussa, today Evonik	1.00
Spinel black	Echtschwarz 100, today HEUCODUR®-Schwarz 9-100	Bayer, today Heubach	3.50
Barium sulphate	Schwerspat	Merck	10.00
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	7.40
Antisettling agent	Wacker HDK N 20	Wacker	0.30
PU-thickener	Rheolate 225	Elementis	0.10
Dispersing agent	Dispex N 40	Ciba	1.80
Thickener	Acrysol RM-55	Rohm and Haas	0.80
Defoamer	Addid 880	Tego Chemie	0.10
<b>Grind.</b>			
			<b>100.00</b>

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.