

Hercules formulation No. P-2C

12/01

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		4.90
Dispersing agent	Dispex GA 40	Ciba	0.30
Glycol ether	Butyl Cellosolve	Union Carbide	2.90
Flash-rust inhibitor	Halox Flash-X 150	Halox	1.30
Defoamer	Drewplus L-405	Drew Ameroid	0.05
Titanium dioxide	Kronos 2310	Kronos	9.60
Magnesium silicate	MP-1250	Barretts Minerals	4.80
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	3.60
Anticorrosive pigment	Zinc oxide		2.90
Barium sulphate	Blanc fixe micro	Sachtleben	4.20
Grind to a finenes of app. 25 microns.			
Acrylic dispersion	Maincote HG-56, 50%	Rohm and Haas	50.90
Ester alcohol	Texanol	Eastman	1.90
Defoamer	Drewplus L-405	Drew Ameroid	0.05
Neutralizing agent	Ammonia, 28%		0.30
Thickener	Natrosol Plus 100, 8% in H ₂ O	Hercules	4.20
	Water		8.10
Add while mixing.			100.00
SPECIFICATIONS			
PVC in %			21.5
Solids in %			51.6

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.