

HEUCOPHOS® ZCP-PLUS

in epoxy powder



Water based

Heubach formulation No. 03249

05/03

FUNCTION	PRODUCT	PRODUCER	PBW
Epoxy powder	Araldit GT 6064	Vantico, today Huntsman	63.40
Curing agent	Härter HT 2844	Vantico, today Huntsman	3.34
Barium sulphate	Blanc fixe N	Sachtleben	16.54
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	5.00
Nickel titanate yellow	HEUCODUR®-Gelb 152	Heubach	0.08
Chromium titanate yellow	HEUCODUR®-Gelb 252	Heubach	0.02
Carbon black	Farbruß FW 200	Degussa, today Evonik	0.02
Titanium dioxide	Kronos 2160	Kronos	8.35
Epoxy powder	Araldit GT 3032	Vantico, today Huntsman	3.00
Degassing agent	Benzoin	Fluka	0.25
			100.00
SPECIFICATIONS			
PVC in %			10.4

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.