

Heubach formulation No. 18456

08/18

FUNCTION	PRODUCT	PRODUCER	PBW
	Demi. water		15.40
Neutralizing agent	Ammonia, 28%		0.10
Dispersing agent	Tamol 165A	Dow	1.90
Surfactant	Triton HW-1000	Dow	0.40
Defoamer	Tego Foamex 1488	Evonik	0.10
Titanium dioxide	Ti-Pure R-900	Chemours	7.70
Magnesium silicate	Talcron MP 10-52	Speciality Minerals	13.65
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	5.10
High Speed Disperse.			
Acrylic	Maincote PR-71, 50%	Dow	43.85
	Demi. water		6.15
Defoamer	Tego Foamex 1488	Evonik	0.10
Coalescing agent	Dowanol Filmer IBT	Dow	2.20
Coalescing agent	Oprtifilm Enhancer 400	Eastman	0.20
Glycol ether	Dowanol DPM	Dow	0.90
Flash-rust inhibitor	Sodium Nitrite, 15% in water		0.85
Neutralizing agent	Ammonia, 15%		0.20
Thickener	Acrysol RM-5000	Dow	1.15
Add.			
Thickener	Acrysol RM-8 W	Dow	0.05
			100.00
SPECIFICATIONS			
PVC in %			30.7
Volume Solids without add			35.8

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.