

Heubach formulation No. 333-20

02/09

FUNCTION	PRODUCT	PRODUCER	PBW
Glycol ether	Dipropylene glycol monomethyl ether		2.05
	Water		6.10
Wetting agent	Tamol 165	Rohm and Haas	1.35
Neutralizing agent	Ammonia, 28%		0.10
Wetting agent	Triton CF-10	Union Carbide	0.15
Defoamer	Tego Foamex 1488	Tego Chemie	0.20
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	7.95
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.90
Iron oxide red	Bayferrox 120 NM	Lanxess	4.50
Calcium carbonate	Atomite	Imerys	9.35
Antisettling agent	Aerosil R 972	Degussa, today Evonik	0.20
Add while mixing.			
Acrylic	Maincote HG-54D	Rohm and Haas	58.00
Neutralizing agent	Ammonia, 28%		0.35
Add to the grind.			
	Water		2.05
Glycol ether	Dipropylene glycol monobutyl ether		3.05
Plasticizer	Dibutyl phthalate	Eastman	1.55
Defoamer	Tego Foamex 1488	Tego Chemie	0.40
Flash-rust inhibitor	Sodium nitrite, 15% in H ₂ O		0.95
Premix.			
PU-thickener	Acrysol RM-12 W	Rohm and Haas	0.40
	Water		0.40
Premix and add while mixing.			
			100.00

HEUCOPHOS[®] ZCP-PLUS / HEUCORIN[®] RZ

in acrylic resin



Water based

Heubach formulation No. 333-20

02/09

SPECIFICATIONS

Vol.-% Anticorrosive pigment reg. pigment/filler	32.0
PVC in %	27.4
PVC / CPVC	0.5
Solids in %	49.5

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.