

Heubach formulation No. 532-11

10/09

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Component A</b>			
Epoxy	Araldite GZ 7071, 75% in xylene	Huntsman	22.15
Epoxy	Araldite GY 783 BD, 100%	Huntsman	16.65
Solvent	N-Butyl alcohol		5.00
Defoamer	Byk-057	Byk-Chemie	0.45
<b>Mix.</b>			
Anticorrosive pigment	HEUCOSIL CTF	Heubach	4.50
Iron oxide red	Bayferrox 130 M	Lanxess	4.65
Aluminium silicate	Sillitin Z 86	Hoffmann Mineral	27.80
<b>Grind with a bead mill.</b>			
			<b>81.20</b>
<b>Component B</b>			
Solvent	Shellsol A	Shell	5.00
Curing agent	Aradur 450 BD, 100%	Huntsman	13.80
<b>Add.</b>			
			<b>18.80</b>
<b>Mix components A and B thoroughly prior to use.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			15.0
PVC in %			24.2
PVC / CPVC			0.6

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.