

HEUCOSIL CTF

in polyester powder



Water based

Heubach formulation No. 590-05

11/10

FUNCTION	PRODUCT	PRODUCER	PBW
Carboxylated polyester resin	Uralac P 885	DSM	65.30
Crosslinker / Hydroxyalkylamide	Primid XL 552	EMS-GRILTECH	3.44
Anticorrosive pigment	HEUCOSIL CTF	Heubach	5.00
Nickel titanate yellow	HEUCODUR®-Gelb 152	Heubach	0.08
Chromium titanate yellow	HEUCODUR®-Gelb 252	Heubach	0.02
Carbon black	FW 200	Evonik	0.02
Titanium dioxide	Kronos 2310	Kronos	8.35
Barium sulphate	Blanc fixe F	Sachtleben	15.79
Matting / Antiblocking agent	Ceridust 9615 A	Clariant	1.00
Levelling agent	Resiflow PV 88	Worlée	1.00
Add.			
			100.00

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.