

Heubach formulation No. 722-04

01/14

FUNCTION	PRODUCT	PRODUCER	PBW
Rheology modifier	Bentone LT Paste, 2% in H ₂ O	Elementis	7.42
Dispersing agent	Nuosperse W-30	Elementis	0.44
Corrosion inhibitor	CHE-COAT-CI LAF 1	Erbslöh	0.34
Glycol ether	Butyl glycol		3.11
Defoamer	Drewplus TS-4380	Ashland	0.05
	Demi. water		0.40
Styrene-acrylic dispersion	Neocryl XK-62, 42%	DSM NeoResins	57.95
Premix.			
Anticorrosive pigment	HEUCOPHOS® CMP	Heubach	5.85
Titanium dioxide	Kronos 2190	Kronos	10.25
Barium sulphate	Blanc fixe N	Sachtleben	2.98
Magnesium silicate	Micro-Talc I.T. Extra	Mondo Minerals	4.38
Carbon black paste	Hostatint-Schwarz GR 30	Clariant	1.09
Grind with a bead mill.			
Defoamer	Drewplus TS-4380	Ashland	0.03
Epoxy ester	Resydrol AX 237 w/70 BG	Allnex	3.10
Glycol ether	Butyl glycol		2.22
Drier	Octa-Soligen Cobalt 10	Borchers	0.05
Neutralizing agent	Ammonia, 25%		0.34
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			30.3
PVC in %			22.1
PVC / CPVC			0.5

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.