

Heubach formulation No. 852-02

04/17

FUNCTION	PRODUCT	PRODUCER	PBW
Styrene-acrylic dispersion	WorléeCryl 7158, 49%	Worlée	49.30
Defoamer	Byk-022	Byk-Chemie	0.40
Wetting agent	Surfynol 104	Air Products	0.40
	Demi. water		9.00
Silicone surfactant	Byk-347	Byk	0.10
Neutralizing agent	Dimethylethanolamine		0.25
Glycol ether	Butyl glycol		1.70
<b>Premix.</b>			
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	12.50
Magnesium silicate	Talk LP30	Lithos	15.10
Titanium dioxide	Kronos 2310	Kronos	8.70
Flash-rust inhibitor	CHE-Coat Ci LNF A4	Erbslöh	0.55
Thickener	BorchiGel 0620/BG 1:1	Borchers	0.10
Defoamer	Tego Foamex 1488	Evonik	0.10
<b>Grind.</b>			
Glycol ether	Dowanol DPM : demi. Water 1:1	Dow	1.80
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			31.5
PVC in %			34.2
PVC / CPVC			0.6
Solids in %			60.5

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.