

Heubach formulation No. 96159

07/96

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Component A</b>			
Epoxy	Epon Resin 828, 100%	Resolution, today Hexion	18.55
Antisettling agent	M-P-A 1078 X	Rheox, today Elementis	0.30
Titanium dioxide	Ti-Pure Rutile R-900	DuPont	2.00
Calcium metasilicate	10 AS Wollastocoat	Nyco Minerals	29.35
<b>Grind.</b>			
Aromatic hydrocarbon	Xylene		3.60
<b>Add while mixing.</b>			
			<b>53.80</b>
<b>Component B</b>			
Curing agent	Ancamide 2353 Curing Agent, 100%	Air Products	10.20
Antisettling agent	M-P-A 1078 X	Rheox, today Elementis	0.30
Melamine resin	Beetle 216-8	Cytec	1.20
<b>Premix.</b>			
Iron oxide red	Bayferrox 222 FM	Bayer	5.95
	LVT 325	Speciality Minerals	6.40
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	11.10
<b>Grind.</b>			
Solvent	Super Hi-Flash Naphtha	Ashland	8.55
Solvent	Diacetone alcohol		2.50
<b>Add.</b>			
			<b>46.20</b>
<b>Mix components A and B thoroughly prior to use.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			

# HEUCOPHOS<sup>®</sup> ZPO

in high solids epoxy



*Solvent based*

Heubach formulation No. 96159

07/96

## SPECIFICATIONS

Solids in %

85.0

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.