

Heubach formulation No. 98161

09/98

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy	D.E.R. 331, 100%	Dow	14.50
Antisettling agent	M-P-A 1078	Elementis	0.25
Iron oxide red	Bayferrox 222 FM	Bayer	3.50
Calcium metasilicate	10 AS Wollastocoat	Nyco Minerals	11.60
Barium sulphate	Barytes BA-25	Engelhard	20.90
Grind.			
Solvent	Aromatic 100	Exxon	7.50
Add while mixing.			
			58.25
Component B			
Curing agent	Ancamide 801 Curing Agent, 100%	Air Products	5.80
Antisettling agent	M-P-A 1078	Elementis	0.10
Levelling agent	Byk-325	Byk-Chemie	0.10
Premix.			
Silica alumina ceramic	Zeeosphere G-400	3M	4.65
Carbon black	SuperJet Lampblack	Elementis	0.10
	LVT 325	Speciality Minerals	5.80
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	10.50
Grind.			
Curing agent	Ancamide 801 Curing Agent, 100%	Air Products	5.40
Solvent	N-Butyl alcohol		7.00
Solvent	Acetone		2.30
Add while mixing.			
			41.75

HEUCOPHOS[®] ZPO

in high solids epoxy



Solvent based

Heubach formulation No. 98161

09/98

FUNCTION	PRODUCT	PRODUCER	PBW
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
Solids in %			83.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.