

Rohm and Haas formulation No. P-71-5

07/95

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		13.00
Wetting agent	Tamol 165	Rohm and Haas	1.00
Wetting agent	Triton CF-10	Union Carbide	0.15
Neutralizing agent	Ammonia, 28%		0.15
Defoamer	Sag 5440	Union Carbide, today GE Silicones	0.15
Premix.			
Iron oxide red	Elementis R-2899 D	Pfizer, today Elementis	5.00
Anticorrosive pigment	Shieldex	Grace	2.50
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	5.00
Magnesium silicate	2610 Talc	Whittaker, Clark and Daniels	10.00
Grind 15 minutes.			
Rheology modifier	Bentone LT paste, 4% in H ₂ O	Rheox, today Elementis	2.50
Grind 5 minutes at lower speed.			
Acrylic dispersion	Maincote PR-71, 50 %	Rohm and Haas	45.45
	Water		3.00
Add grind while mixing.			
Glycol ether	Dipropylene glycol monobutyl ether		0.85
Glycol ether	Dipropylene glycol monomethyl ether		5.00
Solvent	n-Methyl-2-pyrrolidone		1.70
Defoamer	Sag 5440	Union Carbide, today GE Silicones	0.15
Flash-rust inhibitor	Sodium nitrite, 15% in H ₂ O		0.90
PU-thickener	Acrysol SCT-275	Rohm and Haas	1.00
PU-thickener	Acrysol RM-1020	Rohm and Haas	0.40
	Water		2.10

Rohm and Haas formulation No. P-71-5

07/95

FUNCTION	PRODUCT	PRODUCER	PBW
Add while mixing.			
			100.00
SPECIFICATIONS			
PVC in %			26.6

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.