

Zeneca formulation No. D-1185 / today DSM

09/98

FUNCTION	PRODUCT	PRODUCER	PBW
Styrene-acrylic dispersion	Neocryl XK-85, 40%	Zeneca, today DSM	11.10
	Water		6.30
Defoamer	Drew 210-693	Ashland	0.15
Dispersing agent	Disperse-Ayd W 22	Daniel Products, today Elementis	1.30
PU-thickener	Borchigel L 75, today Borchigel L 75 N, 50% in H ₂ O	Borchers	0.60
Flash-rust inhibitor	Ser-AD FA 179	Servo, today Condea Servo	0.50
Glycol ether	Butyl glycol		2.05
Acrylic dispersion	Neocryl A-1094, 40%	Zeneca, today DSM	2.50
Iron oxide black	Bayferrox 318 M	Bayer	4.25
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	6.50
Magnesium silicate	Talkum 20 MOO	Talc de Luzenac	10.80
Carbon black	Special Black 4	Degussa, today Evonik	0.45
Grind with a bead mill, fineness of grind app. 20 microns.			
Styrene-acrylic dispersion	Neocryl XK-85, 40%	Zeneca, today DSM	44.40
	Water		6.10
Ester alcohol	Texanol	Eastman	1.10
Corrosion inhibitor	Nacor 1652	King Industries	1.90
Add grind while mixing.			100.00
SPECIFICATIONS			
PVC in %			24.0
Solids in %			45.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.