

Zeneca formulation No. WB-6039 / today DSM

07/98

FUNCTION	PRODUCT	PRODUCER	PBW
	Water		14.00
Thickener	Natrosol 250 HBR	Hercules	0.10
Premix.			
Defoamer	Foamaster S	Henkel, today Cognis	0.30
Dispersing agent	Byk-155	Byk-Chemie	0.30
Coalescing agent	Pycal 94	ICI	2.30
Magnesium silicate	Mistron Monomix	Talc de Luzenac	18.10
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	4.20
Iron oxide red	Red Iron Oxide R-4098	Hacros, today Elementis	2.80
Grind to a fineness of app. 30 microns, temperature < 40 °C.			
	Water		1.60
Thickener	Acrysol QR-708	Rohm and Haas	0.80
Wetting agent	Surfynol 104 H	Air Products	0.30
Vinyl-acrylic dispersion	Haloflex 202S	Zeneca, today DSM	55.20
Add while mixing.			100.00
SPECIFICATIONS			
PVC in %			26.4
Solids in %			60.9

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.