

Bayer formulation No. SNM 40-23/1

01/86

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Acrylic	Desmophen A 450, 50% in Butyl acetate/Xylene (1:1)	Bayer	40.81
Defoamer	Modaflow, 1% in Xylene	Solutia, today Cytec	1.25
Defoamer	Byk-141	Byk-Chemie	0.25
Premix.			
Antisettling agent	Anti-Terra-U	Byk-Chemie	0.25
Solvent	Solvesso 100	Exxon	4.25
Rheology modifier	Bentone 38	Kronos Titan, today Elementis	0.50
Mix until uniform paste prior to addition.			
Antisettling agent	Aerosil R 972	Degussa, today Evonik	0.25
Aromatic hydrocarbon	Xylene		2.04
Solvent	Butyl acetate		2.04
Solvent	Methoxypropyl acetate		2.04
Titanium dioxide	Bayertitan R-KB-2, today Tronox R-KB-2	Bayer, today Kerr-McGee	8.61
Iron oxide yellow	Bayferrox 3910	Bayer	1.43
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	5.60
Magnesium silicate	Micro-Talc A.T.1	Mondo Minerals	3.04
Barium sulphate	Blanc fixe micro	Sachtleben	21.52
Grind.			
			93.88
Component B			
Curing agent	Desmodur N 75, 75%	Bayer	6.12
Add.			
			6.12
Mix components A and B thoroughly prior to use.			

HEUCOPHOS[®] ZPA

in polyurethane



Solvent based

Bayer formulation No. SNM 40-23/1

01/86

FUNCTION	PRODUCT	PRODUCER	PBW
			100.00
SPECIFICATIONS			
PVC in %			30.0
Solids in %			66.2
Vol.-% Anticorrosive pigment reg. pigment/filler			16.7

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.