

Heubach formulation No. 225-03

05/99

FUNCTION	PRODUCT	PRODUCER	PBW
Polybutadiene dispersion	Polyvest EP-DS 30, 35%	Degussa, today Polymer Latex	64.50
Drier	Nuodex WEB Cobalt 8%	Condea Servo	0.10
Dispersing agent	Ser-AD FA 607	Condea Servo	0.30
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	9.30
Iron oxide red	Bayferrox 130	Bayer	11.50
Magnesium silicate	Talkum Steamic OOS	Talc de Luzenac	13.70
Grind 30 minutes with a bead mill.			
Accelerator	Drymax	Condea Servo	0.10
PU-thickener	Ser-AD FX 1010, 10% in H ₂ O	Condea Servo	0.50
Add to the grind. Adjust pH 8.5 with ammonia.			
			100.00
SPECIFICATIONS			
PVC in %			32.2
PVC / CPVC			0.7
Solids in %			57.5
Vol.-% Anticorrosive pigment reg. pigment/filler			26.3

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.