

Heubach formulation No. 963-04

10/20

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Acrylic Polyol	SETALUX D A 160 SN	Allnex	33.10
Solvent	Solvesso 100		5.00
Aromatic hydrocarbon	Xylene		7.80
Rheology modifier	BENTONE 38	Elementis	0.90
Wetting and Dispersing agent	ANTI-TERRA-204	Byk	0.10
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	11.10
Magnesium silicate	Finntalc M15	MONDO MINERALS	12.60
Quartz	SIKRON SF500	Quarzwerke	11.85
Iron oxide red	BAYFERROX 130 BM	LANXESS	8.35
Grind with a bead mill, fineness of grind app. 20 microns.			
			90.80
Component B			
Polyisocyanate	Desmodur N 75 MPA/X 1:1	Covestro	9.20
			9.20
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			25.0
PVC in %			36.0
PVC / CPVC			0.7
Solids in %			71.5
Crosslinking in %			115.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.