

Heubach formulation No. 00174

08/00

FUNCTION	PRODUCT	PRODUCER	PBW
Soluble alkyd	Cargill 74-7474, 75%	Cargill	7.60
Neutralizing agent	Ammonia, 28%		0.40
Glycol ether	Butyl glycol		1.70
	Water		15.40
<b>Premix.</b>			
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	7.00
Titanium dioxide	Ti-Pure Rutile R-902	DuPont	15.60
<b>Grind.</b>			
Soluble alkyd	Cargill 74-7474, 75%	Cargill	12.20
Neutralizing agent	Ammonia, 28%		0.80
Glycol ether	Butyl glycol		0.80
Solvent	N-Butyl alcohol		0.90
Drier	Cobalt Hydro-Cure II 5%	Mooney Chemicals	0.50
Stabilizer	Activ-8	R.T. Vanderbilt	0.10
	Water		37.00
<b>Premix and add to the grind. Adjust pH 8.5 with ammonia.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Solids in %			37.8
Vol.-% Anticorrosive pigment reg. pigment/filler			37.2

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.