

Heubach formulation No. 555-07

02/11

FUNCTION	PRODUCT	PRODUCER	PBW
Soluble alkyd	WorleeSol 61 P	Worlée	10.45
	Water		16.10
Glycol ether	Dowanol DPM	CG Chemikalien	1.50
Wetting agent	Surfynol 104 E	Air Products	0.10
Defoamer	Byk-022	Byk-Chemie	0.20
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	7.20
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.80
Titanium dioxide	Kronos 2190	Kronos	7.95
Iron oxide black	Bayferrox 318	Lanxess	0.50
Magnesium silicate	Micro-Talc I.T. Extra	Mondo Minerals	3.60
Calcium carbonate	Hydrocarb OG	Omya	5.00
Grind with a bead mill.			
	Water		3.10
Styrene butadiene latex	Synthomer 3020	Synthomer	25.00
Glycol ether	Butyl glycol		4.00
Neutralizing agent	Ammonia, 25%		0.20
Soluble alkyd	WorleeSol 61 P	Worlée	14.00
Drier	Nuodex WEB combi AQ	Elementis	0.30
Add while mixing. Adjust pH 8.5 with ammonia, 25%			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			27.2
PVC / CPVC			0.5
PVC in %			24.3

HEUCOPHOS[®] ZCP-PLUS / HEUCORIN[®] RZ

in hybrid system



Water based

Heubach formulation No. 555-07

02/11

SPECIFICATIONS

CPVC

48.6

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.