

King Industries formulation No. CI-110

10/01

FUNCTION	PRODUCT	PRODUCER	PBW
Dispersing agent	Disperse-Ayd W 30	Elementis	2.90
PU-thickener	Tafigel PUR 55	Münzing	0.30
Titanium dioxide	Ti-Pure Rutile R-900	DuPont	21.00
Defoamer	Agitan 295	Münzing	0.10
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	8.60
	Water		18.50
Premix.			
Epoxy ester	Rezamac WR 7331	Eastman	35.00
Neutralizing agent	Ammonia		2.10
Add while mixing.			
Solvent	Isobutyl alcohol		1.80
Stabilizer	Activ-8	R.T. Vanderbilt	0.10
Drier	Cobalt Hydro-Cure II	OMG	0.30
Drier	Manganese Hydro-Cure II	OMG	0.30
Premix and add to the grind.			
Flash-rust inhibitor	Ser-AD FA 179	Condea Servo	0.30
	Water		6.70
Corrosion inhibitor	Nacorr 1754	King Industries	2.00
Add while mixing.			
			100.00
SPECIFICATIONS			
PVC in %			26.0
Solids in %			56.8

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.