

Evonik Tego formulation No. AC 1000 9 002

10/20

FUNCTION	PRODUCT	PRODUCER	PBW
Reactive methyl silicone resin	SILIKOPHEN AC 1000	Evonik	37.00
Aromatic hydrocarbon	Xylene		18.00
Wetting and Dispersing agent	TEGO Dispers 628	Evonik	2.00
Wetting agent	Tego Wet 270	Evonik	0.10
Rheology modifier	Bentone SD-1	Elementis	2.00
Muscovite mica	Mica TM	Aspanger	15.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	5.00
Copper chromite black spinel	HEUCODUR®-Black 9-100	Heubach	8.00
Antisettling agent	AEROSIL R 972	Evonik	1.60
<b>Grind with a bead mill.</b>			
Solvent	Butyl glycol acetate		2.34
Aromatic hydrocarbon	Xylene		8.96
<b>Add while stirring.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			13.5
PVC in %			24.4
Solids in %			70.0

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.