

Heubach formulation No. 484-03

06/08

FUNCTION	PRODUCT	PRODUCER	PBW
Silicone resin	SILIKOPHEN P 80/MPA	Tego Chemie	35.95
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	4.80
Spinel black	HEUCODUR®-Schwarz 9-100	Heubach	7.80
Carbon black	Printex L	Degussa, today Evonik	1.95
Magnesium aluminium silicate	Plastorit 0000	Luzenac	5.85
Grind.			
Solvent	Butyl acetate		1.60
Rheology modifier	Bentone 38	Elementis	0.30
Wetting agent	Tego Dispers 700	Tego Chemie	0.15
Solvent	Isopropyl alcohol		0.05
Mix until uniform paste prior to addition.			
Solvent	Methoxypropyl acetate		30.55
Solvent	Butyl acetate		11.00
Add while mixing.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			24.6
PVC / CPVC			0.4

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.