

Hoffmann Mineral formulation No. R21401.0 [1]

12/01

FUNCTION	PRODUCT	PRODUCER	PBW
Silicone resin	Silikophen P 50/X	Tego Chemie	55.00
Spinel black	Echtschwarz 100, today HEUCODUR®-Schwarz 9-100	Bayer, today Heubach	8.00
Carbon black	Corax L	Degussa, today Evonik	2.00
Aluminium silicate	Sillitin V 85	Hoffmann Mineral	6.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	6.00
Grind.			
Rheology modifier	Bentone 38	Elementis	0.30
Wetting agent	Tego Dispers 700	Tego Chemie	0.15
Aromatic hydrocarbon	Xylene		1.50
Solvent	Isopropyl alcohol		0.05
Mix until uniform paste prior to addition.			
Aromatic hydrocarbon	Xylene		10.00
Solvent	Butyl acetate		11.00
Add while mixing.			
			100.00

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.