

Tego Chemie formulation No. 304

08/07

FUNCTION	PRODUCT	PRODUCER	PBW
Silicone resin	SILIKOPHEN P 80/X	Tego Chemie	34.40
Spinel black	HEUCODUR®-Schwarz 9-100	Heubach	8.00
Carbon black	Printex L	Degussa, today Evonik	2.00
Magnesium aluminium silicate	Plastorit 0000	Luzenac	6.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	6.00
Grind.			
Rheology modifier	Bentone 38	Elementis	0.30
Aromatic hydrocarbon	Xylene		1.50
Wetting agent	Tego Dispers 700	Tego Chemie	0.15
Solvent	Isopropyl alcohol		0.05
Mix until uniform paste prior to addition.			
Aromatic hydrocarbon	Xylene		30.60
Solvent	Butyl acetate		11.00
Add while mixing.			
			100.00