

Wacker formulation

02/01

FUNCTION	PRODUCT	PRODUCER	PBW
Silicone resin	Silres REN 60	Wacker	43.70
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	5.00
Aluminium paste	Stapa 2	Eckhart	26.30
Antisettling agent	Wacker HDK N 20	Wacker	0.40
Aromatic hydrocarbon	Xylene		24.60
Grind.			
			100.00

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.